

# Konudur 170 BT

Thermo-reactive CIPP lining resin for warm ambient conditions



## PRODUCT PROPERTIES

- Two-component, warm hardening epoxy based resin
- Low-viscosity for enhanced impregnation
- Light-blue pigmentation
- Long-application time
- High-strength even under warm ambient conditions
- Good adhesion to brick, concrete and ceramic
- Can be applied onto dry and moist mineral or metallic substrates
- Dimensional stability under temperatures  $\geq 93$  °C

## AREAS OF APPLICATION

- Impregnation of polyester-needle felt hoses for CIPP liner systems
- No-dig rehabilitation of defective sewer pipes and ducts
- Suitable CIPP resin in accordance with EN 11296-4

## APPLICATION ADVICE

**Substrate preparation:** See data sheet "General Application advice for CIPP liner systems".

**Mixing:** See data sheet "General Application advice for CIPP liner systems". Konudur 170 BT is made up of a base (comp. A) and a hardener (comp. B). The two components have to be carefully mixed to a uniform consistence using a slow-running mechanical stirrer or a suitable static mixer (max. 400 rpm). Mixing by hand and mixing of partial quantities is not allowed.

**Mixing ratio:** See the table "Technical values & product characteristics". The base and hardener component are supplied in packs containing proportionate amounts. Where the components are supplied in drums, the settings on the mixing plant must ensure a correct mixing ratio.

**Application:** See data sheet "General Application advice for CIPP liner systems".

**Curing / Release:** See data sheet "General Application advice for CIPP liner systems". For curing / release times see also the table "Technical values & product characteristics". Curing only by warm-hardening and with a minimum temperature of + 80 °C.

**General information:** The stated times are shortened by high temperatures and extended by low temperatures. A 10 K temperature change doubles or halves the stated times. See also the data sheet "General Application advice for CIPP liner systems".

## TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Mixing ratio	p.b.w.	5 : 1	comp. A : comp. B
Density	kg/dm <sup>3</sup>	approx. 1.46 approx. 0.97 approx. 1.35	component A component B mixture
Working time	hours		
10 kg container		approx. 1 approx. 3.5	at 15° C at 15° C material and ambient temperature
Application conditions	°C	≥ 10 ≤ 35 ≥ 15 ≤ 20	air and substrate temperatures material temperature
Viscosity	mPa · s	approx. 10,000 approx. 600 approx. 8,000	component A component B mixture
Minimum full curing time	minutes		of the impregnated 3 mm polyester needle felt until installation pressure can be released
		approx. 80	at 80° C heating temperature
E-modulus	N/mm <sup>2</sup>	approx. 4,000	EN ISO 178
Compressive strength	N/mm <sup>2</sup>	approx. 105	EN ISO 604
Flexural strength	N/mm <sup>2</sup>	approx. 84	EN ISO 178
Resilient after (full)	days	approx. 7	

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Equipment cleaning agent	MC-Reinigungsmittel U
Colour	light blue
Delivery form	Pair of 30 kg containers 200 kg drum
Storage	Can be stored in original sealed packages at temperatures between 5°C and 30°C in dry conditions for at least 12 months.
Packaging disposal	Videz complètement les emballages perdus. Consultez à ce sujet notre fiche d'information "Reprise des emballages de transport et de vente vides". Nous vous l'enverrons volontiers sur demande.

### Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets.

**Note:** The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2400021146]