MC-TechniFlow 11

superplasticizer and concrete pasticizer for the production of ready-mixed concrete



PRODUCT PROPERTIES	 Intensive dispersion of cement paste 		
	 Decreases the internal frictional forces within the concrete 		
	 Application, spreading and compacting of concrete is made easier 		
	 Reduces early stiffening and hardening 		
	 Long-lasting plasticizing effect 		
	 Retarding effect 		
	 Good homogeneity of the concrete due to the chemical-physical effect 		
	Cost effective dosage		
	Free of corrosion-promoting agents		
AREAS OF APPLICATION	 Ready mixed and job-mixed concrete 		
APPLICATION ADVICE	MC-TechniFlow 11 is a midrange superplasticizer and concrete plasticizer based on a new combina- tion		
	of raw material. It is designed especially for the production of ready-mixed concrete and can be used in		
	combination with all standard cement types.		
	MC-TechniFlow 11 reduces the surface tension of the water. As well as having an intense dispersing ef-		
	fect, this results in strong plastification of the concrete, even if the amounts added are small.		
	The aggregation of cement particles is reduced. The cement is better wetted and finely broken up. This		
	creates easily workable concrete which requires little compaction.		
	Without increasing water content, it is possible to enhance the consistency by several consistency		
	classes.		
	MC Tashui Flaur 11 can be used in combination with other MC administrate, places call our concrete tech		
	MC-TechniFlow 11 can be used in combination with other MC admixtures, please ask our concrete tech- nology-consulting service for further information.		
	MC-TechniFlow 11 can be added on site.		
	Depending on the used type of cement, as well as on the temperature and weather conditions, there		
	might be a retarding side effect. This can be determined with a suitability test.		
	MC-TechniFlow 11 is added to the concrete during mixing. It is most effective when added after the addi-		
	tional water. It is also possible to apply it with the added water. The mixing time should be long enough to		
	allow the admixture to unfold its plasticizing effect during mixing.		
	Storage tanks should be cleaned regularly, to prevent the formation of sediment from inert suspended		
	particles.		
	Please note the "General Information on the Use of Concrete Admixtures".		

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments	
Density	kg/dm³	approx. 1.14		
Recommended dosage range	g	2 - 30	per kg cement	
Chloride content (maximum)	%	< 0.1	mass fraction	
Alkaline content (maximum)	%	< 4.0	mass fraction	
	All technical values are laboratory results determined at $21^{\circ}C \pm 2^{\circ}C$ and 50% relative humidity.			
Self-monitoring	EN ISO 9001			
Type of admixture	Concrete admixture for significant water reduction/liquefaction, EN 934-2:2009+A1:2012 , Water reduc- ing/plasticizing admixture for concrete - EN 934-2:T2			
Designation of admixture	MC-TechniFlow 11			
Colour	brown			
Form	liquid			
Notified body	Karlsruher Institut für Technologie (KIT) Materialprüfungs- & Forschungsanstalt, MPA Karlsruhe, Notified Body number: 0754			
In-company production control	EN ISO 9001, EN 934-2/6			
Colour code of label	yellow/grey			
Delivery form	230 kg drums 1,000 kg container			

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : BZM10

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300019366]