

PRODUCT PROPERTIES

- Free of corrosion promoting components
- Good homogeneity of the concrete due to the chemical-physical effect
- Decreases internal frictional forces within the concrete
- Strong plasticization decreasing the water requirement
- Especially suitable for use in combination with air-entraining agents
- Application, spreading and compaction of concrete is made easier
- Cost effective dosage

AREAS OF APPLICATION

- Ready mixed concrete
- Pre-cast industry
- Freshly made concrete
- Aerated concrete
- Steel fibre concrete

APPLICATION ADVICE

Muraplast FK 99 is a highly plasticizing admixture for the manufacture of concretes with consistencies of classes F2-F6. Strong plasticization can be achieved even with only small dosages.

Muraplast FK 99 can be used in combination with all standard cement types.

Muraplast FK 99 can be added on site. The original consistency can be F2, F3, or F4, if this consistency category has been attained by adding a plasticizing concrete admixture.

Due to its intensive dispersing effect, Muraplast FK 99 has a strong plasticizing effect, even at low dosages. The aggregation of cement particles is reduced. The cement is better wetted and mixed to a smooth mixture. This creates easily workable concrete which requires little compaction.

Muraplast FK 99 greatly reduces the water requirement. By lowering the water/cement ratio, a considerable increase in the early and final concrete strength is possible. Without increasing water content, it is possible to enhance the consistency by several consistency classes, e.g. from F2 to F6.

Muraplast FK 99 can be used with other MC admixtures in concrete, especially with air-entraining agents.

Muraplast FK 99 is added to the concrete during mixing. It is most effective when added after the initial water. It is also possible to apply it with the added water. The mixing time should be long enough to allow the admixture to unfold its plasticizing effect during mixing. Please refer to the relevant regulations, especially if the admixture is added into the supply truck on the construction site.

Please note the "General Information on the Use of Concrete Admixtures".

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density	kg/dm ³	approx. 1.13	± 0.03 kg/dm ³
Recommended dosage range	g	2 - 50	per kg cement
Chloride content (maximum)	%	< 0.1	mass fraction
Alkaline content (maximum)	%	< 3.5	mass fraction

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Self-monitoring	EN ISO 9001
Type of admixture	High range water reducing admixtures/superplasticizing admixture for concrete - EN 934-2:T3.1/3.2 , Water reducing/plasticizing admixture for concrete - EN 934-2:T2
Designation of admixture	Muraplast FK 99
Colour	brown
Form	liquid
Notified body	Karlsruher Institut für Technologie (KIT) Materialprüfungs- & Forschungsanstalt, MPA Karlsruhe, Notified Body number: 0754
In-company production control	EN 934-2/6
Colour code of label	grey/yellow
Delivery form	230 kg drums 1,000 kg container

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : BZM10

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300019858]